



## PRIMER WB 31433 BLACK 3948



Spraying



Waterborne

### PROPERTIES

Top of range polyester waterborne anticorrosion primer:

- Overcoatable with baked-on WB Base Coat AC and SB Base Coat.
- Excellent applicability particularly with electrostatic disk or bell cup.
- Excellent opacifying property.
- Excellent direct adhesion to aluminum.
- Accelerated drying process: 15' RT + 20' at 130°C.
- High spreading rate
- Low VOC

### RELATED BASE COATS

References

Baked-On WB  
Base Coat AC

### BASIS

Waterborne

### SUBSTRATES

Aluminum tubular frames

### TECHNOLOGY

Polyester

### Technical Data

<b>Solids by weight</b>	51 %
<b>VOC</b>	232 g.L <sup>-1</sup>
<b>Spreading rate m<sup>2</sup>/kg</b>	13,4 m <sup>2</sup> / 20 µm dry

